



PRO INDUSTRIAL™

113.05

PRO-CRYL® UNIVERSAL PRIMER B66-310 SERIES

As of 02/01/2014, Complies with:			
OTC	Yes	LEED® 09 CI	Yes
SCAQMD	Yes	LEED® 09 NC	Yes
CARB	Yes	LEED® 09 CS	Yes
CARB SCM 2007	Yes	LEED® 09 S	Yes
MPI#	Yes	NGBS	Yes

CHARACTERISTICS

Pro Industrial Pro-Cryl Universal Primer is an advanced technology, self cross-linking acrylic primer. It is rust inhibitive and designed for both construction and maintenance applications. It can be used as a primer under water-based or solvent-based high performance topcoats.

- Rust inhibitive
- Single component
- Early moisture resistant
- Fast dry
- Low temperature application 40°F
- Interior and exterior use
- Suitable for use in USDA inspected facilities

Color: Off White, Gray, Red Oxide

Recommended Spread Rate per coat:

Wet mils:	5.0 - 10.0
Dry mils:	2.0 - 4.0
~Coverage:	156 - 312 sq ft/gal approximate

NOTE: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.

Drying Time @ 6.0 mils wet 50% RH:

40°F 77°F 120°F

To touch: 2 hrs 40 min 20 min

Tack free: 8 hrs 2 hrs 1 hr

To recoat: 16 hrs 4 hrs 2 hrs

To cure: 45 days 30 days 14 days

Drying time is temperature, humidity, and film thickness dependent.

Finish: Low sheen

Flash Point: N/A

Shelf Life: 36 months, unopened
Store indoors at 40°F to 100°F.

Tinting: Do not tint

B66W310 (may vary by color)

VOC (less exempt solvents):

96 g/L; 0.80 lb/gal

As per 40 CFR 59.406 and SOR/2009-264, s.12

Volume Solids: 36% ± 2%

Weight Solids: 49% ± 2%

Weight per Gallon: 10.2 lb

RECOMMENDED SYSTEMS

Waterborne topcoat:

- 1-2 cts. Pro Industrial High Performance Acrylic
- or Pro Industrial Waterborne Catalyzed Epoxy
- or Pro Industrial Multi-Surface Acrylic
- or Pro Industrial Hi-Bild Waterbased Epoxy
- or Pro Industrial Pre-Catalyzed Epoxy

Solvent borne topcoat:

- 1-2 cts. Pro Industrial High Performance Epoxy
- or Pro Industrial Urethane Alkyd

Pro Industrial Pro-Cryl Universal Primer B66W310 Off White is GREENGUARD GOLD certified for low chemical emissions into indoor air during product usage. For more information, visit ul.com/gg.

System Tested: (unless otherwise indicated)

- Substrate: Steel
- Surface Preparation: SSPC-SP10
- 1 ct. Pro Industrial Pro-Cryl Universal Primer
- 1 ct. Pro Industrial High Performance Acrylic

Adhesion:

- Method: ASTM D4541
- Result: 500 psi

Result: Passes

Moisture Condensation Resistance:

- Method: ASTM D4585, 100°F, 1250 hours

Result: Passes

Corrosion Weathering:

- Method: ASTM D5894, 10 cycles, 3360 hours
- Result: Passes

Pencil Hardness:

- Method: ASTM D3363
- Result: H

Direct Impact Resistance:

- Method: ASTM D2794
- Result: >140 in. lbs.

Salt Fog Resistance:

- Method: ASTM B117, 1250 hours
- Result: Passes

Dry Heat Resistance*:

- Method: ASTM D2485
- Result: 200°F

Provides performance comparable to products formulated to federal specification: AA50557 and Paint Specification: SSPC-Paint 23.

Flexibility:

- Method: ASTM D522, 180° bend, 1/4" mandrel

*Suitable for intermittent dry heat resistance up to 300°F when used as a system with Sher-Cryl HPA

PRO INDUSTRIAL™
PRO-CRYL® UNIVERSAL PRIMER



SURFACE PREPARATION

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.

Do not use hydrocarbon solvents for cleaning.

Iron and Steel - Minimum surface preparation is Hand Tool Cleaning per SSPC-SP2. Remove all oil and grease from the surface per SSPC-SP1. For better performance, use Commercial Blast Cleaning per SSPC-SP6.

Aluminum - Remove all oil, grease, dirt, oxide and other foreign material per SSPC-SP1.

Galvanizing - Allow to weather a minimum of six months prior to coating. Solvent Clean per SSPC-SP1. When weathering is not possible, or the surface has been treated with chromates or silicates, first Solvent Clean per SSPC-SP1 and apply a test patch. Allow paint to dry at least one week before testing adhesion. If adhesion is poor, brush blasting per SSPC-SP7 is necessary to remove these treatments. Rusty galvanizing requires a minimum of Hand Tool Cleaning per SSPC-SP2, prime the area the same day as cleaned.

Previously Painted Surfaces - If in sound condition, clean the surface of all foreign material. Smooth, hard or glossy coatings and surfaces should be dulled by abrading the surface. Apply a test area, allowing paint to dry one week before testing adhesion. If adhesion is poor, additional abrasion of the surface and/or removal of the previous coating may be necessary. Retest surface for adhesion. If paint is peeling or badly weathered, clean surface to sound substrate and treat as a new surface as above.

APPLICATION

Refer to the MSDS before using

Temperature: 40°F minimum
 120°F maximum
 (air, surface, and material)
 At least 5°F above dew point

Relative humidity: 85% maximum

The following is a guide. Changes in pressures and tip sizes may be needed for proper spray characteristics. Always purge spray equipment before use with listed reducer. Any reduction must be compatible with the existing environmental and application conditions.

Reducer: Water

Airless Spray

Pressure2000 psi
 Hose 1/4" ID
 Tip015" - .019"
 Filter 60 mesh
 ReductionNot recommended

Conventional Spray

Gun Binks 95
 Fluid Nozzle..... 66
 Air Nozzle 63PB
 Atomization Pressure60 psi
 Fluid Pressure25 psi
 ReductionAs needed up to 5% by volume

Brush Nylon/Polyester
 ReductionNot recommended

Roller3/8" woven
 ReductionAs needed up to 5% by volume

If specific application equipment is listed above, equivalent equipment may be substituted.

CLEANUP INFORMATION

Clean spills and spatters immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with Mineral Spirits to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using Mineral Spirits.

HOTW 02/17/2014 B66W310 32 96

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin. The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.